



C16 UNIHARDENER HS FAST

Rapid hardener - HS

A) DESCRIPTION AND FIELDS OF APPLICATION:

All purpose high solid catalyst that allows to obtain higher thickness with fewer coats and a fast hardening. Absolutely non-yellowing, compatible with all clear coats and coloured finishing enamels, both acrylic and polyurethane based.

Suggested temperature of application : 18-25°C.

B) TECHNICAL DATA:

Composition	Polyisocyanic resins and solvents
Specific weight	0,986 ± 0,03 kg/l
Available colours	Colourless
Safety data	See safety data sheet

C) PROCESSING :

Mixing ratio 2:1 by volume : two parts Enamel or Clear coat with one part C16 catalyst.

With Enamels or Clear coats requiring mixing ratio of 3:1 or 4:1, it's possible to replace their original catalyst with C16 catalyst used at 2:1 mixing ratio.

D) CAUTIONS:

- * The catalysts for 2K products contain Isocyanates and react to damp.
- * Keep containers well closed. Be sure that all working instruments and mixing tanks are perfectly dry.

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained

INDUSTRIA CHIMICA REGGIANA - I.C.R. S.p.A.

42124 Reggio Emilia - Via M. Gasparini, 7 - Tel. +39 0522 517803 - Fax +39 0522 514384 - e-mail: icr@icrsprint.it - www.icrsprint.it

Uff. Comm.le Italia: 42124 Reggio Emilia - Via Neviani, 5 - Tel. +39 0522 517803 - Fax +39 0522 231819

International Department: 42124 Reggio Emilia - Via Neviani, 5 - Tel. +39 0522 513738 - Fax +39 0522 512446

Stabilimento: 42124 Reggio Emilia - Via M. Gasparini, 7 - Tel. +39 0522 517803 - Fax +39 0522 514384

Stabilimento: 26817 S. Martino in Strada (LO) - Via del Commercio, 1 - Tel. +39 0371 475313 - Fax +39 0371 475370

CAPITALE SOC. € 557.820,00 - R.E.A. N. 82109 M. R.E. 000534 - Reg. Imprese, COD. FISC. e PART. IVA 00140910357