



H69 VANTIX CLEAR UHS

UHS 2K Acrylic Clearcoat

Completely new to the field of car-repair clearcoats due to the product's rheological properties that notably prevent sagging while ensuring excellent spread.

Other main features include: ease of application, excellent spreading, high gloss and fast drying time. It is especially suitable for bodyshop repair work using waterbourne base coats as it cuts effects caused by the absorption of these latter.

The EU VOC limit for this product ready-to-use (product category IIB(d)) is 420 g/l.

B) TECHNICAL DATA:

Composition	Hydroxylated acrylic resins
Specific weight	0,975 ± 0,03 kg/l
Available colours	Colourless, transparent
Safety data	Refer to the safety sheet

C) SURFACE PREPARATION :



* Matt base coat for two coats of solvent-based paint

* Matt base coat for two coats of water-based paint

D) CAUTIONS:



- * Mix well before use.
- * Comply with the application ratios.
- * Do not use the product at temperatures below 10°C.
- * Keep in a cool, dry place.



E) PROCESSING:



2:1 with C63/C67/C68/C69 Hardener, potlife 45' at 20°C.



Do not dilute.
18" DIN 4 a 20°C.



1,3-1,4 mm 2,5-3,5 bar
Apply a light coat followed by a full coat to obtain a final dry thickness of 50 – 60 micron.



1,4-1,5 mm 3-4 bar
1+1/2 = 50-60 micron



5'-10'



at 23°C : Time Dryng : 7-8 h. Buffing Time: 15-16 h
at 60°C : Time Dryng : 25'. Buffing Time : 30' after cooling.



12' at 1 mt.

F) TOOLS CLEANING:

* With thinner for polyurethane products

G) RECOATING :

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained