



R00 KIT-TEX P

Fiberglass repair kit with paste hardener

A) DESCRIPTION AND FIELDS OF APPLICATION:

Especially meant for repairing fiberglass parts, metal and other supports; with paste hardener when quick drying is required.

B) TECHNICAL DATA:

Composition	Unsaturated polyester resin
Specific weight	1,1 ± 0,1
Available colours	Colourless
Safety data	See Safety data sheet

C) PROCESSING :

The repairing job can be easily done by applying on the spot to be repaired a first layer of fiberglass mat suitably shaped according to the imperfections. With a brush wet the mat with resin previously mixed with 2% hardener. Repeat the operation for every layer you want to add, being careful to impregnate well the fiberglass mat with resin.

As the catalyzed resin has been used, prepare some more- just the quantity to be used within 5-6 minutes. The complete hardening will occur within 1 hour depending on thickness, temperature and catalyst ratio; maximum performance will be obtained after 24 hours.

D) CAUTIONS:

- * Mix well the resin with 2% of paste hardener
- * Do not exceed with the hardener
- * Do not utilize the product at temperatures below 5°C
- * Store in a cool and dry place.

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained

INDUSTRIA CHIMICA REGGIANA - I.C.R. S.p.A

42100 Reggio Emilia - Via M. Gasparini, 7 - Tel. +39 0522 517803 - Fax +39 0522 514384 - e-mail: icr@icrsprint.it - www.icrsprint.it

Uff. Comm.le Italia: 42100 **Reggio Emilia** - Via Neviani, 5 - Tel. +39 0522 517803 - Fax +39 0522 231819

International Department: 42100 **Reggio Emilia** - Via Neviani, 5 - Tel. +39 0522 513738 - Fax +39 0522 512446

Stabilimento: 42025 **Cavriago** - Via Nizzola, 5 - Tel. +39 0522 371818 - Fax +39 0522 575110

Stabilimento: 06074 **Perugia** - Via Trasimeno Ovest, 159/Z/13 - Tel. +39 075 518611 - Fax +39 075 5186125

CAPITALE SOC. € 557.820,00 - R.E.A. N. 82109 M. R.E. 000534 - Reg. Imprese, COD. FISC. e PART. IVA 00140910357